

Table S1. T_g values obtained for binary systems studied.

x_1	$T_g / ^\circ\text{C}$			
	NAP (1) – IND (2)	NAP (1) – IBU (2)	NAP (1) – PRO (2)	IND (1) – PAR (2)
0.1	43.2	-41.1	25.6	24.2
0.2	37.3	-35.9	24.4	27.5
0.3	31.3	-31.1	22.5	28.8
0.4	30.4	-25.0	21.4	31.8
0.5	27.0	-21.4	19.2	33.5
0.6	22.7	-	-	35.0
0.7	19.8	-	-	31.2
0.8	-	-	-	37.3
0.9	-	-	-	38.8




Figure S1. XRPD patterns of APIs studied. Based on comparison of diffractograms with the Cambridge structural database the following crystal structures were identified. IND: form γ (INDMET), IBU: form I (IBPRAC), NAP: form I (COYRUD11), PAR: form I (HXACAN34), and PRO: form I (HAXHET01).




Figure S2. Tammann plots of studied systems. ΔH_E represents the enthalpy obtained by integration of eutectic peak.