

Novel PDI-NH/PDI-COOH Supramolecular Junction for Enhanced Visible-Light Photocatalytic Phenol Degradation

Yongzhang Xu ^{1,†}, Xingrui Luo ^{1,†}, Fulin Wang ¹, Wentao Xiang ¹, Chensheng Zhou ¹, Weiya Huang ¹, Kangqiang Lu ¹, Shaoyu Li ^{1,*}, Man Zhou ^{2,*} and Kai Yang ^{1,*}

¹ Jiangxi Provincial Key Laboratory of Functional Molecular Materials Chemistry, School of Chemistry and Chemical Engineering, Jiangxi University of Science and Technology, Ganzhou 341000, China

² School of Pharmaceutical Sciences, Gannan Medical University, Ganzhou 341000, China

* Correspondence: 9120150135@jxust.edu.cn (S.L.); baiyuwawa-zhouman@163.com (M.Z.); yangkai@jxust.edu.cn (K.Y.)

† These authors contributed equally to this work.

Table S1. Total organic carbon (TOC) levels in the photocatalytic degradation of phenol solution of 5 mg/L over PP1.

Time (h)	0	1	2	3	4	5
TOC (mg/L)	5.13	4.11	3.03	1.92	0.94	0.002




Figure S1. N2 adsorption-desorption diagrams of P-NH, P-COOH and PP-1.




Figure S2. SEM image of PP-1 for post-reaction.