



Figure S2. (a, b) SEM images of the modifying nanostructured palladium coating based on nanowires synthesized by two-step electrodeposition from a solution of H_2PdCl_4 with $\text{C}_{19}\text{H}_{42}\text{BrN}$ at a current density of $2.5 \mu\text{A cm}^{-2}$ for 30–40 s and a current density of 0.35 mA cm^{-2} for 3–5 min.