

Table S1. Compositional ananlysis of the *E.hirae* biopolymer.

Components	Composition(%)
Total Sugar	38.0
Hexoseamines	26.00
Uronic acid	8.70
Pyruvic acid	9.3
Proteins	18.6