

Communication

# Branched Versus Linear Structure: Lowering the CO<sub>2</sub> Desorption Temperature of Polyethylenimine-Functionalized Silica Adsorbents


Jannis Hack, Seraina Frazzetto, Leon Evers, Nobutaka Maeda \* and Daniel M. Meier \*

Institute of Materials and Process Engineering (IMPE), School of Engineering (SoE), Zurich University of Applied Sciences (ZHAW), CH-8400 Winterthur, Switzerland; hacj@zhaw.ch (J.H.), serainafrazzetto@outlook.com (S.F.), ever@zhaw.ch (L.E.)

\* Correspondence: maeo@zhaw.ch (N.M.), meid@zhaw.ch (D.M.M.)

## Desorption of CO<sub>2</sub> at 45 °C

Figure S1 shows the desorption kinetics of 30 wt% LPEI/SiO<sub>2</sub> at 45 °C. the complete desorption took ca. 3000 s (50 min).



**Figure S1.** The desorption of CO<sub>2</sub> for 30 wt% LPEI/SiO<sub>2</sub> (300 mg) at 45 oC.