

Article

The AC Soft Magnetic Properties of FeCoNi_xCuAl (1.0 ≤ x ≤ 1.75) High-Entropy Alloys

Zhongyuan Wu ¹, Chenxu Wang ¹, Yin Zhang ¹, Xiaomeng Feng ¹, Yong Gu ^{1,2}, Zhong Li ³, Huisheng Jiao ⁴, Xiaohua Tan ^{1,*} and Hui Xu ^{1,*}

¹ Institute of Materials, School of Materials Science and Engineering, Shanghai University, Shanghai 200072, China; wzy951122@gmail.com (Z.W.); wcx123581@163.com (C.W.); zhangyin0208@163.com (Y.Z.); fengxiaomeng96@163.com (X.F.); gy2018@hznu.edu.cn (Y.G.)

² Qianjiang College, Hangzhou Normal University, Hangzhou 310036, China

³ College of Materials and Environmental Engineering, Institute for Advanced Magnetic Materials, Hangzhou Dianzi University, Hangzhou 310018, China; hanying880205@163.com

⁴ Tescan China, Ltd., Shanghai 201112, China; Huisheng.Jiao@tescanchina.com

* Correspondence: tanxiaohua123@163.com (X.T.); Huixu8888@shu.edu.cn (H.X.); Tel.: +86-021-563-378-87 (H.X.)

Table S1. Direct current (DC) soft magnetic properties of FeCoNi_xCuAl (1.0 ≤ x ≤ 1.75) high-entropy alloys.

x	M _s (Am ² /kg)	μ _i	μ _m	P _u (J/m ³)	B _r (mT)	H _c (A/m)
1.00	78.69	45.6	150.0	2019	293.6	998.8
1.25	75.60	132.4	300.8	737.2	235.3	383.0
1.50	59.33	213.4	383.3	241.1	127.8	178.3
1.75	54.44	181.1	289.4	205.2	88.7	167.8



© 2019 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).