

Article

A Comparison Study on the Characteristics of Nanofibrils Isolated from Fibers and Parenchyma Cells in Bamboo

Xiaofeng Zhang ^{1,2}, Hanxiao Huang ^{1,2}, Yan Qing ¹, Hankun Wang ^{2,3,*} and Xingong Li ^{1,*}

¹ College of Materials Science and Engineering, Central South University of Forestry and Technology, Changsha, 410004, China; zhangxf@icbr.ac.cn (X.Z.); huanghx@icbr.ac.cn (H.H.); qingyan0429@163.com (Y.Q.)

² Institute of New Bamboo and Rattan Based Biomaterials, International Center for Bamboo and Rattan, Beijing, 100102, China

³ SFA and Beijing Co-built Key Lab for Bamboo and Rattan Science & Technology, Beijing, 100102, China

* Correspondence: wanghankun@icbr.ac.cn (H.W.); lxgwood@163.com (X.L.)

Table S1. CrI (%) of samples in different stage from fibers and parenchyma cells.

Samples	CrI (%)	Samples	CrI (%)
F	39.39	P	26.53
F-LCSR	42.55	P-LCSR	37.21
F-CSR	43.16	P-CSR	37.82
F-LCNF	23.78	P-LCNF	26.10
F-CNF	28.48	P-CNF	28.95

Table S2. T_{onset} and T_{max} values for samples from fibers and parenchyma cells.

Samples	T_{onset} (°C)	T_{max} (°C)
F-LCSR	313.44	332.82
F-CSR	327.43	349.07
P-LCSR	302.43	324.97
P-CSR	331.69	353.79