

Article

Study of Partially Transient Organic Epidermal Sensors

Supporting Materials

To evaluate the printing ability of PEO substrate, contact angle measurement was done by dropping 5 μL PEODOT:PSS solution on PEO substrate, then measured the contact angle. As seen from Figure 1, the contact angle is 55.653 $^\circ\text{C}$.




Figure S1. Contact angle between PEODOT:PSS solution droplet on PEO substrate.