

Comparison of the properties of bio-polyols based on white mustard (*Sinapis alba*) oil containing boron and sulfur atoms obtained by various methods and checking their influence on the flammability of rigid polyurethane/polyisocyanurate foams

Marcin Borowicz^{1,*}, Marek Isbrandt¹, Joanna Paciorek-Sadowska¹ and Paweł Sander¹

¹ Department of Chemistry and Technology of Polyurethanes, Faculty of Materials Engineering, Kazimierz Wielki University, J. K. Chodkiewicza Street 30, 85-064 Bydgoszcz, Poland

* Correspondence: m.borowicz@ukw.edu.pl (M.B.); Tel.: +48-52-34-19-286

1. Apparent density of foams modified by new bio-polyols**Table S1.** Apparent density of obtained foams.

Foam symbol		Apparent density (kg/m ³)
Ref.		51.48 ± 1.32
MP1.01		52.93 ± 2.14
MP2.01		51.02 ± 1.74
MP2.02		50.12 ± 1.05
MP2.03		47.39 ± 2.21
MP2.04		45.89 ± 1.14
MP2.05		45.03 ± 1.37
MP3.01		49.99 ± 0.89
MP3.02		48.02 ± 1.14
MP3.03		47.78 ± 1.43
MP3.04		46.83 ± 1.75
MP3.05		46.13 ± 1.54