

Supplementary File S1

Data tables used to create the 3D graphs

Table S1. Influence of liquid-to-solid ratio and MT content on compressive strength at 28 days

		liquid to solid ratio		
		0.5	0.63	0.75
MT content, wt.%	25	1.21	5.35	11.10
	50	3.80	5.66	15.82
	75	2.69	9.40	6.99

* The values in red are the mean values of compressive strength.

Table S2. Influence of Na:Al ratio and MT content on compressive strength at 28 days.

		Na:Al ratio		
		0.5	0.63	0.75
MT content, wt.%	25	1.21	5.54	11.10
	50	15.82	3.80	5.66
	75	9.40	6.99	2.69

* The values in red are the mean values of compressive strength.