

Supporting Information

Table S1. Physicochemical properties of various zeolites.

Samples	Si/Al	S _{BET}	S _{micro}	S _{ext}	V _{Tot}	Acidity
		(m ² /g)	(m ² /g)	(m ² /g)	(cm ³ /g)	(mmol/g)
SAPO-18	0.21*	587	571	16	0.25	1.77
H-LTL	3.12	360	345	15	0.19	0.68
H-FAU-Y	2.04	421	398	23	0.26	0.87

*Si/(Al+P)