


1473 K, 86.4 ks



Sample	Phase	Ti	Zr	Nb	Hf	Ta
1473 K, 86.4 ks	1	1.1 (\pm 1)	13 (\pm 1.5)	2.9 (\pm 2.3)	76 (\pm 10.8)	7 (\pm 4.7)
	2	11.5 (\pm 0.5)	6.1 (\pm 1.3)	24.3 (\pm 0.6)	5.1 (\pm 0.7)	53 (\pm 1.4)
	3	23.9(\pm 0.8)	40.2 (\pm 2.8)	4.6 (\pm 1.3)	17.6 (\pm 2.3)	13.7 (\pm 4)