

Supplementary Information

Optimizing polymer solar cells using non-halogenated solvent blends

Guler Kocak¹, Desta Gedefaw^{1,2}, and Mats R. Andersson^{1,*}

¹ Flinders Institute for Nanoscale Science and Technology, Flinders University, Sturt Road, Bedford Park, Adelaide, SA 5042, Australia

² School of Biological and Chemical Sciences, The University of South Pacific, Laucala Campus, Suva, Fiji

* Correspondence: mats.andersson@flinders.edu.au; Tel.: +61-8-82013585

Table S1: The integrated currents from EQE compared to the Jsc from I-V measurement of corresponding devices.

Solvent	Integrated Jsc from EQE (mA/cm ²)	Jsc (mA/cm ²)
o-xylene	2.2	2.3
o-xylene + 2% MN	9.7	9.9
o-xylene + 3% PN	9.9	10.4
o-xylene + 3% DIO	8.2	8.9
o-xylene + 2% CN	5.9	6.4