

## Supplementary Information


# Cross-Linking Optimization for Electrospun Gelatin: Challenge of Preserving Fiber Topography

Chiara Emma Campiglio <sup>1</sup>, Selene Ponzini <sup>2</sup>, Paola De Stefano <sup>2</sup>, Giulia Ortoleva <sup>2</sup>, Lorenzo Vignati <sup>2</sup> and Lorenza Draghi <sup>1,2,\*</sup>

<sup>1</sup> Department of Chemistry, Materials and Chemical Engineering “G. Natta”, Politecnico di Milano, via Mancinelli 7, 20131 Milan, Italy; Chiaraemma.campiglio@polimi.it

<sup>2</sup> INSTM—National Interuniversity Consortium of Materials Science and Technology, Local Unit Politecnico di Milano, Piazza Leonardo da Vinci 32, 20133 Milan, Italy; selene.ponzini@mail.polimi.it (S.P.); paola.destefano@polimi.it (P.D.S.); giulia.ortoleva@mail.polimi.it (G.O.); lorenzo4.vignati@mail.polimi.it (L.V.)

\* Correspondence: lorenza.draghi@polimi.it; Tel.: +39-0223993184



**Figure S1.** Cross-linking process for EDC/NHS and GTA solution method. Gelatin samples were mounted on a mandrel and immersed in cross-linking solutions for the selected time. After cross-linking, solvent evaporation was carried out under three different conditions: air drying, slow drying in a closed vessel and slow drying in a closed vessel with silica gel beads, in order to select the most suitable condition for fiber topography preservation. .