



Figure S1. AFM topography of P3HT:PCBM films on (a) PEDOT:PSS and (b) MoO₃. Root-mean-square (RMS) roughness of P3HT:PCBM film on PEDOT:PSS and MoO₃ were 1.92 nm and 1.58 nm, respectively.



© 2020 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).