

Supporting information

Effect of Tea polyphenols on the Melt Grafting of Glycidyl Methacrylate onto Polypropylene

Xin Zheng ^{1,2}, Lina He ², Guipeng Yu ^{1,*} and Yongjin Li ^{2,*}

¹ College of Chemistry and Chemical Engineering, Central South University, Changsha 410083, Hunan, China

² College of Material, Chemistry and Chemical Engineering, Key Laboratory of Organosilicon Chemistry and Material Technology, Ministry of Education, Hangzhou Normal University, Hangzhou 311121, Zhejiang, China

* Correspondence: yongjin-li@hznu.edu.cn (Y. Li); Tel.: +86-571-2886-7026; gilbertyu@csu.edu.cn (G. Yu); Tel.: +86-731-8883-6961

Table S1. The MFR of PP-DCP-C blends with different tea polyphenols (C) loadings.

Sample	MFR (g/10 min)
PP-DCP-C=100-0.5-0	967
PP-DCP-C=100-0.5-0.5	614
PP-DCP-C=100-0.5-1	342