

Removal of Various Hazardous Materials Using a Multifunctional Biomass-Derived Hydroxyapatite (HAP) Catalyst and Its Antibacterial Effects

Sanha Jang ¹, Kyeongmun Park ¹, Sehwan Song ², Haksoo Lee ³, Sungkyun Park ², BuHyun Youn ^{3,*}, Kang Hyun Park ^{1,4,*}

¹ Department of Chemistry, Pusan National University, Busandaehak-ro 63beon-gil, Geumjeong-gu, Busan, 46241, Korea; jangs0522@naver.com (S.J.); pkmkm951@naver.com (K.P.)

² Department of Physics, Pusan National University, Busandaehak-ro 63beon-gil, Geumjeong-gu, Busan, 46241, Korea; sehwan song465@gmail.com (S.S.)


³ Department of Biological Sciences, Pusan National University, Busandaehak-ro 63beon-gil, Geumjeong-gu, Busan, 46241, Korea; hs950303@gmail.com (H.L.)

⁴ SoulDot Co., Ltd, Pusan National University, Busandaehak-ro 63beon-gil, Geumjeong-gu, Busan 46241, Korea

* Correspondence: bhyoun72@pusan.ac.kr (B.Y.); Tel.: +82-51-510-2264, and chemistry@pusan.ac.kr (K.H.P.) Tel.: +82-51-510-2238

Table of Contents:

Scheme S1. Schematic image of antibacterial tests using Gram negative and Gram positive.....	S1
Figure S1. Histogram of South Korean fishery production and byproducts.....	S2
Figure S2. Oyster shells that have not been treated in South Korea.....	S3
Figure S3. HAADF-STEM image and elemental mapping images of CaO	S4
Figure S4. XPS spectra of CaO and HAP.....	S5
Table S1. ICP data table for RT conditions of various metal cation adsorption.....	S6
Table S2. ICP data table for various acidic condition of various metal cation adsorption.....	S7
Table S3. Calculation of antibacterial efficiency of <i>E. coli</i> and <i>S. aureus</i>	S8



Scheme S1. Schematic image of antibacterial tests using Gram negative and Gram positive, respectively.




Figure S1. Histogram of South Korean fishery production and byproducts [44].



Figure S2. Oyster shells that have not been treated in South Korea. The photo was taken by Sanha Jang.




Figure S3. (a) HAADF-STEM image of CaO and (b-d) elemental mapping images of CaO. The bars indicate 100 nm, respectively.




Figure S4. Survey spectrum of (a) CaO and (b) HAP powders and deconvoluted (c) Ca 2p and (d) O 1s spectrum. The vertical dotted lines indicate the reference binding energy.

Table S1. ICP data table for RT condition of various metal cation adsorption

	Cr	Mn	Ni	Cu	Cd	Ba	Pb
Initial concentration (ppm)	115.39	85.44	98.47	112.60	99.63	114.79	103.52
Final concentration (ppm)	48.56	28.80	61.89	79.78	26.03	64.25	7.49
RSD (%)	0.75	1.90	0.54	0.38	0.95	1.02	5.30
Removal efficiency (%)	57.9	66.3	37.1	29.1	73.9	44.0	92.8

Table S2. ICP data table for various acidic condition of various metal cation adsorption

	Cr			Cd			Pb		
	pH7	pH5	pH4	pH7	pH5	pH4	pH7	pH5	pH4
Final concentration (ppm)	0.33	64.26	63.63	0	84.08	35.74	13.68	4.52	7.91
RSD (%)	2.12	0.80	2.28	0.65	2.65	0.73	3.97	1.30	1.87
Average removal efficiency (%)	63.0			59.9			91.6		

Table S3. Calculation of antibacterial efficiency of *E. coli* and *S. aureus* for 24 h

	Antibacterial efficiency (%)	
Concentration of HAP	<i>E. coli</i>	<i>S. aureus</i>
5 mM	74.4	78.1
10 mM	89.6	96.0