

The Use of Premixed Calcium Silicate Bioceramic Sealer with Warm Carrier-Based Technique: A 2-Year Study for Patients Treated in A Master Program

Fausto Zamparini ^{1,2}, Andrea Spinelli ¹, Filippo Cardinali ³, Pietro Ausiello ⁴, Maria Giovanna Gandolfi ² and Carlo Prati ^{1,5,*}

¹ Endodontic Clinical Section, Dental School, Department of Biomedical and Neuromotor Sciences, University of Bologna, Bologna, 40125, Italy

² Laboratory of Green Biomaterials and Oral Pathology, Dental School, Department of Biomedical and Neuromotor Sciences, University of Bologna, Bologna, 40125, Italy

³ Private Practice, Ancona, 60123, Italy; filocardinali@gmail.com

⁴ School of Dentistry, University of Naples Federico II, Naples, 80131, Italy

⁵ Dean Master in Endodontics, Dental School, University of Bologna, Via San Vitale 59, 40125 Bologna, Italy

* Correspondence: carlo.prati@unibo.it




Figure S1. Graphs reporting the cases where sealer apical extrusion occurred. Periapical radiographs during the follow-up at 6, 12 and 24 months revealed the complete radiographical resorption of 3 extrusions in Ceraseal-TF group, one at 6 months and 2 at 12 months respectively. Differently, AH Plus-TF extrusions were stable along all the 24 months follow-up.

Table S1: Quantification of radiographic apically extruded sealer in relation to PAI. Ceraseal +TF group displayed radiographic resorption of the sealer, while AH Plus+TF displayed no modification of extruded sealer.

	Ceraseal-TF				AH Plus-TF			
	PAI 1-2		PAI 3-5		PAI 1-2		PAI 3-5	
	T0	T24	T0	T24	T0	T24	T0	T24
0mm	18	19	21	23	14	14	19	19
0.1-1mm	1	0	1	1	1	1	2	2
1.1-3mm	0	0	1	1	4	4	2	2
≥ 3mm	0	0	3	1	2	2	0	0