

Development of New Natural Lipid-Based Nanoparticles Loaded with Aluminum-Phthalocyanine for Photodynamic Therapy Against Melanoma

Victor Carlos Mello^{1,2,3}, Victor Hugo Sousa Araújo⁴, Karen Letycia Rodrigues de Paiva^{2,3}, Marina Mesquita Simões^{2,3}, Dafne Caroline Marques^{2,3}, Nelice Roberta da Silva Costa⁵, Isadora Florêncio de Souza², Patricia Bento da Silva⁵, Igor Santos⁶, Raquel Almeida⁶, Kelly Grace Magalhães⁶, Sebastião William da Silva⁷, Alexandre Silva Santos⁷, Fabiane Veiga-Souza^{8,10}, Paulo Eduardo Narcizo Souza⁹, Marina Arantes Raddichi^{2,5}, João Paulo Figueiró Longo⁵, Jennifer Thayanne Cavalcante de Araújo⁴, Luis Alexandre Muehlmann¹⁰, Marlus Chorilli⁴ and Sônia Nair Bão^{2,*}

¹ Postgraduate Program in Animal Biology, Institute of Biological Sciences, Department of Genetics and Morphology, Institute of Biological Sciences, University of Brasília, Brasília, DF 70910-900, Brazil

² Laboratory of Microscopy and Microanalysis, Department of Cell Biology, Institute of Biological Sciences, University of Brasília, Brasília, DF 70910-900, Brazil

³ COOIL Institute, Brasília, DF 72622401, Brazil

⁴ School of Pharmaceutical Sciences, São Paulo State University, Araraquara, 14800-903, Brazil

⁵ Laboratory of Nanobiotechnology, Department of Genetics and Morphology, Institute of Biological Sciences, University of Brasilia, Brasilia 70910-900 , Brazil

⁶ Laboratory of Immunology and Inflammation, Department of Cell Biology, University of Brasilia, Brasilia, DF 70910-900, Brazil

⁷ Optical Spectroscopy Laboratory, Institute of Physics, University of Brasilia, Brasilia, DF 70910-900, Brazil

⁸ Laboratory of Protein Chemistry and Biochemistry, Department of Cell Biology, Institute of Biology, University of Brasília, Brasília, DF 70910-900, Brazil

⁹ Laboratory of Electron Paramagnetic Resonance, Institute of Physics, University of Brasília, Brasília, DF 70910-900, Brazil

¹⁰ Faculty of Ceilandia, University of Brasilia, Brasilia, DF 70910-900, Brazil

* Correspondence: smbao@unb.br

Table S1. Stability of SLN-AlPc by the parameters of DH, PDI and PZ, for 1, 90 and 176 days, at room temperature, 4°C and 37°C

	Day 1	Day 90	Day 176
Room Temperature			
DH (nm)	35.64 ± 0.913	57.53 ± 1.195	60.41 ± 3.41
ZP (mV)	-5.61 ± 0.925	-6.63 ± 0.249	-5.09 ± 0.732
Pdl	0.123 ± 0.013	0.118 ± 0.009	0.192 ± 0.027
4°C			
DH (nm)	35.64 ± 0.913	54.36 ± 1.628	49.12 ± 2.198
ZP (mV)	-5.61 ± 0.925	-7.64 ± 0.826	-5.89 ± 1.012
Pdl	0.123 ± 0.013	0.149 ± 0.018	0.192 ± 0.027
37°C			
DH (nm)	35.64 ± 0.913	257.3 ± 24.60	Phase separation
ZP (mV)	-5.61 ± 0.925	-6.63 ± 0.249	
Pdl	0.123 ± 0.013	0.346 ± 0.084	

DH: Hydrodynamic diameter; PDI: Polydispersity index; and PZ: Potential zeta




Figure S1. FTIR spectra of the (a) SLN-AlPc and (b) SLN formulation, (c) murumuru butter and (d) AlPc free




Figure S2. Normal Raman spectra of the (a) SLN-AlPc formulation and (b) SLN formulation, (c) murumuru butter and (d) AlPc free.




Figure S3. Zoom, at different spectral ranges, of the SERS spectra of SLN-AlPc formulation (black lines) and physical mixture (AlPc+SLN), (red lines) of samples (i) Gly-solution and (ii) 2Gly@PEG/NPs, and (iv) normal Raman spectrum of Gly-solution.

(see Figure S3 - SLN-AlPc: black lines and AlPc+SL: red lines).




Figure S4. Fluorescence (**A**, **B**) and absorbance (**C**) spectrum of SLN-AlPc. A = Ex:660 nm and B = Ex:350 nm