

Supplementary Materials

Table S1. Static, advancing and receding CA values and their corresponding hysteresis CA for the treated stones.

Treatment	θ_s (°)	θ_A (°)	θ_R (°)	Hysteresis (°)
TV100	73 ± 5	88 ± 5	52 ± 4	35 ± 3
BS290	111 ± 4	121 ± 3	105 ± 3	15 ± 4
UCA-T	97 ± 11	104 ± 2	80 ± 4	24 ± 3
UCA-TS	107 ± 9	105 ± 6	86 ± 9	20 ± 3
UCA-T+F	121 ± 5	118 ± 3	101 ± 4	17 ± 3
UCA-TS+F	122 ± 2	118 ± 2	101 ± 6	17 ± 3