

Supplement To:

Growth Induced Magnetic Anisotropy in Yttrium Iron Garnet Films on Yttrium Aluminum Garnet Substrates

Ying Liu,^{1,2} Peng Zhou,² Rao Bidthanapally,¹ Jitao Zhang,³ Wei Zhang,¹ Michael R. Page,⁴ Tianjin Zhang,² and Gopalan Srinivasan¹

¹ Department of Physics, Oakland University, Rochester, MI 48309, USA

² Department of Materials Science and Engineering, Hubei University, Wuhan 430062, China

³ College of Electrical and Information Engineering, Zhengzhou University of Light Industry, Zhengzhou 450002, China

⁴ Materials and Manufacturing Directorate, Air Force Research Laboratory, Wright-Patterson Air Force Base, Dayton, Ohio 45433, USA

Corresponding author: G. Srinivasan

email: srinivas@oakland.edu




Figure S1: SEM cross sectional image of YIG film grown on (110) YAG, film growth time is 30 min.




Figure S2: SEM cross sectional image of YIG film grown on (110) YAG, film growth time is 60 min.




Figure S3: SEM cross sectional image of YIG film grown on (110) YAG, film growth time is 90 min.




Figure S4: SEM cross sectional image of YIG film grown on (110) YAG, film growth time is 120 min.




Figure S5: SEM cross sectional image of YIG film grown on (111) YAG, film growth time is 30 min.




Figure S6: SEM cross sectional image of YIG film grown on (111) YAG, film growth time is 60 min.




Figure S7: SEM cross sectional image of YIG film grown on (111) YAG, film growth time is 90 min.





Figure S8: SEM cross sectional image of YIG film grown on (111) YAG, film growth time is 120 min.



Element	Weight %	Atomic %
Al K	0.00	0.00
Fe L	51.21	62.56
Ga L	0.00	0.00
Y L	48.79	37.44
Totals	100.00	

Film composition: $\text{Y}_{3.0}\text{Fe}_{5.0}\text{O}_{12}$

Figure S9: Representative data showing energy dispersive x-ray spectroscopy for composition of YIG films. The results are for the 380 nm thick YIG on (100) YAG.









Figure S10: M vs H hysteresis loops for in-plane H for films on (110) YAG.

Figure S11: M vs H hysteresis loops for in-plane H for films on (111) YAG.






Figure S12: Normalized magnetization vs H hysteresis loops for out-of-plane H for YIG films on (100) YAG. Results are shown for a series of film deposition times.




Figure S13: Normalized magnetization vs H hysteresis loops for out-of-plane H as in Figure S12 for YIG films on (110) YAG.








Figure S14: Normalized magnetization vs H hysteresis loops for out-of-plane H for YIG films on (111) YAG.



$$\gamma = 2.79 \text{ GHz/kOe,}$$

$$4\pi M_{\text{eff}} = 1.551 \text{ kOe}$$

Figure S15. (Left) Profiles of amplitude scattering matrix S_{21} vs H showing FMR in 120 nm thick YIG/(100) YAG for in-plane H along [001] direction of YAG. (Right) Theoretical fit to data on resonance frequency and field for estimation of magnetic parameters for the film.



$$\gamma = 2.77 \text{ GHz/kOe,}$$

$$4\pi M_{\text{eff}} = 1.636 \text{ kOe}$$

Figure S16. (Left) Profiles of amplitude scattering matrix S_{21} vs H showing FMR in 170 nm thick YIG/(100) YAG for in-plane H along [001] direction of YAG. (Right) Theoretical fit to data on resonance frequency and field for estimation of magnetic parameters for the film.







Figure S17. (Left) Profiles of amplitude scattering matrix S_{21} vs H showing FMR in 380 nm thick YIG/(100) YAG for in-plane H along [001] direction of YAG. (Right) Theoretical fit to data on resonance frequency and field for estimation of magnetic parameters for the film.



$$\gamma = 2.79 \text{ GHz/kOe,}$$

$$4\pi M_{\text{eff}} = 1.494 \text{ kOe}$$

Figure S18. (Left) Profiles of amplitude scattering matrix S_{21} vs H showing FMR in 145 nm thick YIG/(110) YAG for in-plane H along [001] direction of YAG. (Right) Theoretical fit to data on resonance frequency and field for estimation of magnetic parameters for the film.





Figure S19. (Left) Profiles of amplitude scattering matrix S_{21} vs H showing FMR in 205 nm thick YIG/(110) YAG for in-plane H along [001] direction of YAG. (Right) Theoretical fit to data on resonance frequency and field for estimation of magnetic parameters for the film.