

# Supporting Information

## Processing and Mechanics of Aromatic Vitrimeric Composites at Elevated Temperatures and Healing Performance

Tanaya Mandal <sup>1</sup>, Unal Ozten <sup>2</sup>, Louis Vaught <sup>3</sup>, Jacob L. Meyer <sup>4</sup>, Ahmad Amiri <sup>5,6</sup>, Andreas Polycarpou <sup>3,5</sup>  
and Mohammad Naraghi <sup>2,\*</sup>

- 1 Department of Materials Science & Engineering, Texas A&M University, College Station, TX 77843, USA;  
tmandal90@tamu.edu
- 2 Department of Aerospace Engineering, Texas A&M University, College Station, TX 77843, USA;  
uozten@tamu.edu
- 3 J. Mike Walker '66 Mechanical Engineering Department, Texas A&M University, College Station,  
TX 77843, USA; lovaught@tamu.edu (L.V.); andreas-polycarpou@utulsa.edu (A.P.)
- 4 ATSP Innovations, Houston, TX 77055, USA; jacob.l.meyer@atspinnovations.com
- 5 Russell School of Chemical Engineering, The University of Tulsa, Tulsa, OK 74104, USA;  
ahmad-amiri@utulsa.edu
- 6 Department of Mechanical Engineering, The University of Tulsa, Tulsa, Oklahoma 74104, USA,  
ahmad-amiri@utulsa.edu

\* Correspondence: [naraghi@tamu.edu](mailto:naraghi@tamu.edu)

**Table S1. Average Mode I Fracture Toughness and Average Healing Efficiency**

<b>Sample #</b>	<b><math>G_{IC-v}</math> (J/m<sup>2</sup>)</b>	<b>Average <math>G_{IC-v}</math> (J/m<sup>2</sup>)</b>	<b><math>G_{IC-h}</math> (J/m<sup>2</sup>)</b>	<b>Average <math>G_{IC-v}</math> (J/m<sup>2</sup>)</b>	<b>Healing Efficiency (%)</b>	<b>Average Healing Efficiency (%)</b>
1	318.3	264.45± 36.80	339	288.88± 38.44	106.5	109.48 ± 7.92
2	257.9		276.9		107.4	
3	241.8		292.7		121.03	
4	239.8		246.9		103.0	